



**SOUTHWEST GAS CORPORATION**

® ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff 

*Approved By:* Jerome T. Schmitz 

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	1 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

---

**1. SCOPE**

This specification covers ASTM A-53, Grade B, seamless and electric-resistance welded carbon steel pipe in nominal pipe sizes (NPS) of 3/8-inch through 3 1/2-inch. This steel pipe is used for various uses including the manufacture of pipe nipples in Southwest Gas Material Specification B-4.

**2. APPLICABLE DOCUMENTS**

- 2.1 ASTM International (ASTM) A-53M-10 (Oct. 2010), "Standard Specification for Pipe, Steel, Black and Hot-Dipped, Zinc Coated Welded and Seamless."
- 2.2 ASTM International (ASTM) A-370, "Mechanical Testing of Steel Products, Annex II, Steel Tubular Products."
- 2.3 ASTM International (ASTM) A-530, "Standard Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe."
- 2.4 ASTM International (ASTM) A-700, "Standard Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment."
- 2.5 ASTM International (ASTM) A-751, "Standard Methods, Practices and Definition for Chemical Analysis of Steel Products."
- 2.6 SWG Corporation Material Specification (MS) B-4, "Pipe Nipples, Threaded and Plain End."
- 2.7 United States Department of Transportation (DOT), Code of Federal Regulations (CFR), Title 49, Part 192, "Transportation of Natural and Other Gas by Pipeline; Minimum Safety Standards."

**NOTE:** Unless otherwise specified, the editions of the above documents incorporated by DOT 49 CFR 192 are applicable. Documents not incorporated by DOT 49 CFR 192 will be the most recent edition.



**SOUTHWEST GAS CORPORATION**

® ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff 

*Approved By:* Jerome T. Schmitz 

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	2 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

---

**3. TERMINOLOGY**

3.1 General

- 3.1.1 "Southwest Gas," "Southwest" or "SWG" wherever used in this specification and other related documents will refer exclusively to Southwest Gas Corporation.
- 3.1.2 The terms "approve," "as approved," "satisfactory," "as directed," "or equal," or other similar terms wherever used in this specification and other related documents, will mean "as determined by Southwest Gas," unless specifically stated otherwise.
- 3.1.3 "Product Information Package" or "PIP" wherever used in this specification and other related documents will mean the required information that a manufacturer must submit to SWG to determine if the product is suitable for use by SWG, unless specifically stated otherwise.

**4. MATERIAL AND MANUFACTURING**

- 4.1 Pipe purchased under specification will be manufactured, as a minimum, in accordance with ASTM A-53 and additional requirements as defined in this specification.
- 4.2 Pipe manufactured to this specification will be furnished in the following types and grades:
  - Type E, Grade B, Electric-resistance welded (ERW) or,
  - Type S, Grade B, Seamless.
- 4.3 Killed steel, made by one or more of the following processes: electric furnace, open hearth or basic oxygen, will be used exclusively in the manufacturing of pipe covered in this specification.
- 4.4 Jointers are not permitted.
- 4.5 Pipe end specifications are given in Southwest Gas' MS B-4 and will be specified in the purchase order.



**SOUTHWEST GAS CORPORATION**

® ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff 

*Approved By:* Jerome T. Schmitz 

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	3 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

---

**4. MATERIAL AND MANUFACTURE (Cont'd)**

- 4.6 The pipe will be visually examined and will be determined to be free of defects as defined by Section 20 of ASTM A-53. Surface imperfections that penetrate more than 12.5% of the nominal wall thickness will be considered defects. The pipe surface will be free from scale, dents and injurious defects.
- 4.7 Defects in the pipe may be repaired in accordance with ASTM A-530 with written consent from Southwest Gas. Repair welding of the weld seam of Type E is prohibited.

**5. PERFORMANCE REQUIREMENTS**

- 5.1 The material will conform to the tensile requirements of ASTM A-53; Grade B. Testing procedures will conform to the requirements of ASTM A-370. All pipe tests must include yield strength, ultimate tensile strength and elongation determinations at room temperature.
- 5.2 A flattening test will be performed on all pipe larger than 2-inch in accordance with ASTM A-53 for both seamless and ERW. Southwest retains the right to require flattening tests on pipe smaller than 2-inch.
- 5.3 All pipe will be subjected to a hydrostatic pressure test. The test pressure will be in accordance with ASTM A-53 and are shown in Table X2.2 of that document. The test pressure need not exceed 2500 psig.
- 5.4 Tests required by ASTM A-53 and A-530 not contained in this specification will be performed per ASTM requirements. Southwest Gas may, at their discretion, request the results of such tests if specified on the purchase order.
- 5.5 The composition of pipe furnished to this specification, as determined by heat analysis according to ASTM A-751, will conform to ASTM A-53, Table 1 and 2, for Grade B.



**SOUTHWEST GAS CORPORATION**

ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff

*Approved By:* Jerome T. Schmitz

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	4 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

**6. DIMENSIONS AND TOLERANCES**

- 6.1 Pipe diameter and wall thickness dimensions and tolerances will conform to Table X2.2 in ASTM A-53.
- 6.2 Individual lengths may be requested per SWG MS B-4
- 6.3 Unless a minimum or maximum length is specified on the materials requisition and purchase order, the following tolerances in length shall apply:

Nominal Length	Minimum Length	Minimum Average Lengths Of Each Order Item	Maximum Length
20 ft (SRL)	9.0 ft	17.5 ft	22.5 ft
40 ft (DRL)	14.0 ft	35.0 ft	45.0 ft
60 ft (TRL)	21.0 ft	52.5 ft	65.0 ft
80 ft	28.0 ft	70.0 ft	85.0 ft

**TABLE A-4.1**

**7. INSPECTION**

- 7.1 Successful review of the Product Information Package (PIP), as well as any future reference by SWG to the Seller's part number or internal code number in any future contract or purchase, will mean only that no conflict with the specification was found and will not relieve the Seller from meeting all the requirements of this specification.
- 7.2 SWG retains the option to inspect the manufacture and testing of any and all materials, products or systems referenced in this specification that are sold to SWG.
- 7.3 SWG will make appropriate inspections and tests of any and all materials, products or systems supplied to this specification. SWG will have the right, at their option, to reject any material which fails to conform to this specification. Any such rejection may take place at the manufacturer facility; the supplier's warehouse or any subsequent delivery location, before or after SWG assumes possession. Notice of the rejection will be made promptly to the supplier by SWG. The defective product will be replaced or returned for credit at the manufacturer's expense.



**SOUTHWEST GAS CORPORATION**

® ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff 

*Approved By:* Jerome T. Schmitz 

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	5 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

---

**7. INSPECTION** (Cont'd)

7.4 Any changes in the manufacturing of previously approved materials, products or systems described in this material specification for sale to SWG, must be approved by SWG's Engineering Staff. **Failure to obtain SWG's approval may be cause for rejection and disqualification as an approved supplier.**

**8. CERTIFICATION**

The manufacturer's or supplier's certification will be furnished to Southwest. This certification will state that samples representing each lot have been manufactured, tested, and inspected in accordance with this specification and that all requirements have been met. When requested or specified in the purchase order or contract, a report of test results will be provided. The supplier will provide the results of all tests outlined in Section 5 and 6 in tabular form according to grade and heat number.

Upon the request of Southwest, the certification of an independent third party indicating conformance to this specification may be considered at Southwest's expense.

**9. SAFETY DATA SHEETS**

In accordance with law, the Seller will supply Safety Data Sheets for all applicable items supplied under this specification to the following:

- 1) The Receiving Location
- 2) Engineering Staff
- 3) Southwest Gas Corporation  
Corporate Safety  
Mail Station LVA-530  
P.O. Box 98510  
Las Vegas, NV 89193-8510



**SOUTHWEST GAS CORPORATION**

® ENGINEERING STAFF

**MATERIAL SPECIFICATION**

*Prepared By:* Engineering Staff 

*Approved By:* Jerome T. Schmitz 

<b>Section No:</b>	MS A-4
<b>Page No.:</b>	6 of 7
<b>Issue Date:</b>	03/01/16
<b>Superseded Date:</b>	02/05/15

**PIPE AND TUBING**

Pipe, Steel, ASTM A-53 (Black)

---

**10. PRODUCT MARKING**

The pipe manufactured to this specification will be marked in accordance with ASTM A-53. This will include ASTM designation, grade, type, manufacturers name or trademark, size, weight and heat number.

Pipe sold to Southwest Gas will have SWG's purchase order number marked on each length.

**11. PACKAGING AND PACKAGE MARKING**

Packaging and package marking will conform to ASTM A-700 unless otherwise specified by Southwest Gas. All products covered in this specification will be packaged in a manner to prevent damage during transportation and storage.

**12. STOCK CLASSIFICATION DESCRIPTION**

PIPE, BLACK, ASTM A-53, GRADE B, \_\_\_\_\_ (TYPE S OR TYPE E); \_\_\_\_\_ INCH OD X WT; \_\_\_\_\_ (SRL, DRL, TRL OR FEET); \_\_\_\_\_ ENDS (PLAIN OR ACCORDING TO MS B-4; MAX LENGTH \_\_\_ FT, MIN LENGTH \_\_\_ FT. (OPTIONAL); FOR USE IN MS B-4 ONLY.